



Technische Information / Technical information

Bandtype PVC 35/364 B



Tradition and innovation since 1929

Einsatzgebiete // fields of application	Kartoffelverarbeitung, Steine und Isolationsmaterial, Baumaterial: Glas, Gips, Isolationsmaterial, Holz Potato processing, stones and insulation material, building material: glass, plaster, insulations material, wood
Eigenschaften // properties	Querstabil, fettresistent Transverse stability, fat resistant
Verbindungsarten // types of joining	Fingerverbindung finger joint
Gewebe // fabric	Polyester, monofil
Lagenzahl // number of plies	2
Zugkraft bei 1% Dehnung N/mm // tractive power for 1% tension N/mm	10
Beschichtung Tragseite // coating material carrying side	PVC, 65 Shore A // PVC, 65 Shore A
Beschichtung Laufseite // coating material running side	PVC // PVC
Farbe // colour	Blau // blue
antistatisch // antistatic	Nein // no
prägefähig // embossable	Nein // no
Lebensmitteignung // certificate about food applicability	FDA, USDA
Dicke mm // thickness mm	3,25
Gewicht g/m ² // weight g/mm ²	3.400
max. Breite mm // max. width mm	2.000
min. Walzen-Ø mm // min. roller-Ø mm	40
Temperaturbeständigkeit °C // temperature stability °C	-10 bis +110
Reibungskoeffizient auf Stahl Tragseite // friction value on steel carrying side	-
Reibungskoeffizient auf Stahl Laufseite // friction value on steel running side	0,35
Wärmedurchgangswert W/m ² // heat through value W/m ² .0.00	-